# **Maclac Product Data Sheet**

R.J. MCGLENNON CO. INC. 198 UTAH STREET SAN FRANCISCO, CA 94103

PHONE (415) 552-0311 FAX (415) 552-8055

## 204 SERIES WWX-2000 275 WATER WHITE SANDING SEALER LACQUER

## Description

204 series are fast drying, low VOC water white lacquer sanding sealer. It is designed for use where air quality regulations require using 275 G/L VOC for wood finishes. This compliance gloss lacquer has exceptional toughness. It is recommended for use on all wood surfaces. See the Product Line information Sheet for more details.

### **Specifications**

Weight per Gallon: 7.67 Coating VOC: 275 G/L 2.29 Lb/gal

Solids by Weight %: 19.96 Material VOC: 62 G/L 0.52 Lb/gal Solids by Volume %: 14.78 VOC Weight Ratio =0.33 Lb VOC/Lb Solid

Coverage @ 1 mil: 237 SqFt./Gal. Viscosity: 18 - 22 Seconds Zahn 2

### **Surface Preparation**

Apply over properly sanded wood surfaces. Ensure that any stains used are compatible with this system. Surfaces must be clean and free of dirt, grease and water. Remove any wax or old finish. The use of any other product as a sanding sealer will severely limit the durability and the re-coat properties of these products. No Maclac paint product has ever contained any lead. But if you are preparing previously painted surfaces with unknown paints please observe the following precautions. Warning! If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NOISH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

# Mixing & Thinning

Product as supplied is ready to spray. No further thinning is required or recommended. However, if any reduction is desired, then we recommend thinning with Acetone, as this will not change the VOC content. Additional thinning with a non-exempt thinner will raise the VOC content. Thoroughly mix the material by stirring or shaking prior to application.

## Application & Dry

This product is designed for spray application only. Note: all sanding dust must be removed prior to application of any of these very low VOC lacquers - sanding dust will not be absorbed into the coating, which will cause a rough surface and lost of sheen. These may be applied with conventional, airless, air-assist airless or HVLP spray equipment. It is best applied as a wet coat for flow and leveling. Apply sufficient material to wet the surface and hold a good "wet edge" which will minimize orange peel. Do not exceed 5 mils total film build (includes sealers and topcoats). This product will dry to sand within about 25 minutes when applied under standard conditions to about 1 mil dry film.

## **Performance & Durability**

Forms an easy sanding sealer coat for wood. Designed as part of a water white lacquer system. Whereas any nitrocellulose lacquer system will yellow with time, R.J. McGlennon Co. recommends using the water white system over white stains in order to slow the natural yellowing process.

#### **Environmental & Safe Handling**

Warning: flammable mixture. Do not use near heat, sparks, flames, or any ignition sources. Do not cut empty containers. Use only with adequate ventilation. Dispose of any product only in accordance with all applicable regulations. See separate material safety data sheet for full details.

Page 1 of 1

#### LIMITED WARRANTY

The information contained herein is offered to assist customers in determining whether our products are suitable for their applications. We request that customers examine our products before use and satisfy themselves as to their suitability. We warrant that our products will meet our written specifications. Since application circumstances, substrate condition and product intermix are beyond our control, we cannot guarantee results under all possible situations. R.J. McGlennon Co. Inc. makes no representation as to the results the user will achieve.

Technical advice furnished by seller or any seller's agents shall not constitute a warranty. Any liability arising out of any condition resulting from the use of any R.J. McGlennon Co. Inc. product shall be limited to

Technical advice furnished by seller or any seller's agents shall not constitute a warranty. Any liability arising out of any condition resulting from the use of any R.J. McGlennon Co. Inc. product shall be limited to replacement of such product.