

Maclac Product Data Sheet

R. J. MCGLENNON CO. INC.
198 UTAH STREET
SAN FRANCISCO, CA 94103

PHONE (415) 552-0311
FAX (415) 552-8055

50 SERIES QU-244 WHITE AQUATEK PRIMER

Description

This quality waterborne primer applies easily, flows out well, and dries to a tough film with excellent build. This Waterborne primer is lead and chromate free.

Specifications

These represent product as supplied

Weight per Gallon:	10.67	Coating VOC:	199 G/L 1.66 Lb/gal
Solids by Weight %:	43.68	Material VOC:	62 G/L 0.52 Lb/gal
Solids by Volume %:	27.33	Color:	WHITE
Coverage @ 1 mil:	438 SqFt./Gal.	Gloss = flat @ 60 Deg	
Viscosity:	600 -800 CPS		

Surface Preparation

This Primer must be applied directly to clean, dry metal surfaces. Remove dust, grease, oil, or other surface contaminants prior to application.

No Maclac paint product has ever contained any lead. But if you are preparing previously painted surfaces with unknown paints please observe the following precautions. Warning! If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

Mixing & Thinning

This Primer should be used as supplied. If lower viscosity is required, heating the material to 75° F is usually adequate and preferred over the addition of water, water may be used, but 5-10% maximum only is recommended.

Application & Dry

This Primer is easily applied with conventional, airless and HVLP spray equipment. One full wet coat usually produces an excellent finish. If more build is required, Aquatek should be lightly sanded prior to second application. Total dry film thickness should not exceed approximately 4-5 mils. The drying time for sanding or recoat under standard conditions is 40 minutes to 1 hour. Lower temperatures and higher humidity may extend the dry time to 2 hours.

Performance & Durability

This Primer forms a very durable finish with an excellent balance of flexibility and hardness. This Primer is ideal for shop applications. It will give very good corrosion resistance.

Environmental & Safe Handling

Aquatek is non-flammable and the dried film is non-toxic. Use only with adequate ventilation. Dispose of any product only in accordance with all applicable regulations. Clean-up can usually be accomplished with water or a water-detergent combination. See material safety data sheet for full details.

LIMITED WARRANTY

The information contained herein is offered to assist customers in determining whether our products are suitable for their applications. We request that customers examine our products before use and satisfy themselves as to their suitability. We warrant that our products will meet our written specifications. Since application circumstances, substrate condition and product intermix are beyond our control, we cannot guarantee results under all possible situations. R.J. McGlennon Co. Inc. makes no representation as to the results the user will achieve. Technical advice furnished by seller or any seller's agents shall not constitute a warranty. Any liability arising out of any condition resulting from the use of any R.J. McGlennon Co. Inc. product shall be limited to replacement of such product.