

Maclac Product Data Sheet

R. J. MCGLENNON CO. INC.
198 UTAH STREET
SAN FRANCISCO, CA 94103

PHONE (415) 552-0311
FAX (415) 552-8055

MACLAC T-198 REFLOW THINNER

Description

This Lacquer Thinner is a blend of solvents suitable for thinning most nitrocellulose based lacquers. It is formulated to produce a good viscosity reduction while imparting good flow and leveling to the coating.

Note: beginning June 2003 It is suitable for use with both Maclac Standard Lacquers and Low VOC Lacquers.

Specifications

Weight per Gallon: 7.10 VOC content: 851 G/L (7.09 Lb/gal)

Composite Vapor Pressure (calculated) 40.7 mm Hg. @68Deg.F.
Flash Point = 58 Deg F.

Note: the following definitions are included to help the user exercise proper care in the safe handling of this product:

Vapor Pressure is an expression of the pressure exerted by vapors of a liquid at a standard temperature (measured in millimeters (mm) of Mercury (Hg) at 68°F)

The greater the Vapor pressure, the faster it will evaporate.

Flash Point is the lowest temperature at which vapor evaporating from a liquid can form a combustible mixture with the air. If the liquid is below this temperature, it will not evaporate enough to form a combustible mix. The lower the flash point, the greater the care needed in the handling of these products. Note, regardless of the flash point of any solvent, users must always keep all solvents away from any heat, sparks or open flames and any possible combustion source.

Environmental & Safe Handling

Air quality regulations are not consistent throughout the country, nor are they consistent within the State of California. Always check local air quality regulation prior to using this product. Warning: flammable mixture. Do not use near heat, sparks, flames, or any ignition sources. Do not cut empty containers. Use only with adequate ventilation. Dispose of any product only in accordance with all applicable regulations. See product material safety data sheet for more information.

LIMITED WARRANTY

The information contained herein is offered to assist customers in determining whether our products are suitable for their applications. We request that customers examine our products before use and satisfy themselves as to their suitability. We warrant that our products will meet our written specifications. Since application circumstances, substrate condition and product intermix are beyond our control, we cannot guarantee results under all possible situations. R.J. McGlennon Co. Inc. makes no representation as to the results the user will achieve.

Technical advice furnished by seller or any seller's agents shall not constitute a warranty. Any liability arising out of any condition resulting from the use of any R.J. McGlennon Co. Inc. product shall be limited to replacement of such product.